



DAFIBRE 155 AL

Rectangular conductor of aluminium, covered with glassfibre yarn, class 155

Product name:

Dafibre 155 1 AL
 Dafibre 155 2 AL
 Dafibre 155 3 AL

Specifications:

Internal LWW or customer specification

UL approval:

Not approved

Class: 155

Temperature index $\geq 155^{\circ}\text{C}$ acc. to experience
 Heat shock: $\geq 175^{\circ}\text{C}$

Insulation:

1-3 layers of glass-fibre yarn
 Impregnation: Polyurethane

Properties:

- Excellent resistance to mechanical stress
- Suitable in lightweight designs

Field of application:

- Generators
- Large motors
- Magnet coils
- Welding equipment

Standard packaging:


Drum 500 and 630

Shelf life:

5 years, under normal ambient conditions

Conductor material

EN 1715 - EN AW1370 [Al 99.7]



$T - t =$ Increase in thickness

$W - w =$ Increase in width

Conductor corner radius

Nominal thickness of conductor (mm)		Corner radius (mm)	Tolerance
Over	Up to and including		
-	1,00	0,5 nominal thickness	+/- 25%
1,00	1,60	0,50	+/- 25%
1,60	2,24	0,65	+/- 25%
2,24	3,55	0,80	+/- 25%
3,55	-	1,00	+/- 25%

Conductor tolerances

Nominal width or thickness of the conductor (mm)		Tolerance +/- (mm)
Over	Up to and including	
-	3,15	0,030
3,15	6,30	0,050
6,30	12,50	0,070
12,50	-	0,100

DAFIBRE 155 AL

Rectangular conductor of aluminium, covered with glassfibre yarn, class 155

Insulation increase


Designation	Nominal width of conductor	Increase in thickness	Increase in width
Dafibre 155 1 AL	$2,00 \leq w \leq 3,15$	$0,16 \pm 0,04$	max. 0,20
	$3,15 < w \leq 6,30$	$0,18 \pm 0,04$	max. 0,22
	$6,30 < w \leq 12,50$	$0,21 \pm 0,05$	max. 0,26
	$12,50 < w \leq 20,50$	$0,24 \pm 0,06$	max. 0,30
Dafibre 155 2 AL	$2,00 \leq w \leq 3,15$	$0,27 \pm 0,06$	max. 0,33
	$3,15 < w \leq 6,30$	$0,30 \pm 0,07$	max. 0,37
	$6,30 < w \leq 12,50$	$0,35 \pm 0,08$	max. 0,43
	$12,50 < w \leq 20,50$	$0,39 \pm 0,08$	max. 0,47
Dafibre 155 3 AL	$2,00 \leq w \leq 3,15$	$0,44 \pm 0,09$	max. 0,53
	$3,15 < w \leq 6,30$	$0,46 \pm 0,09$	max. 0,55
	$6,30 < w \leq 12,50$	$0,50 \pm 0,11$	max. 0,61
	$12,50 < w \leq 20,50$	$0,64 \pm 0,14$	max. 0,78

Properties for DAFIBRE 155 AL

Main characteristics	Test method	Interval	Acceptance criteria
Electrical properties			
Conductor resistance	IEC 60851 - 5.3	1)	$0,02817 \Omega\text{mm}^2/\text{m}$
Conductivity	1/R	1)	$> 35,5 \text{ m}/(\Omega\text{mm}^2)$
Breakdown voltage	IEC 60851 - 5.4	All sizes	350 V
- Dafibre 155 1 AL			560 V
- Dafibre 155 2 AL			750 V
- Dafibre 155 3 AL			
Mechanical properties			
Elongation	IEC 60851-3.3	$t \leq 3,15$	$\geq 15\%$
		$t > 3,15$	$\geq 20\%$
Flexibility	IEC 60851-3.5	All sizes	10 x thickness
- Bending flatwise			
Adherence	IEC 60851-3.5	All sizes	10 % stretch, no loss of adhesion
-Stretch			

1. Dependence of dimension is expressed by the unit

Dimension range



The technical data included is up to date at the time of printing.

LWW reserves the right to make any amendments deemed necessary

Ed.A(4)

LWW group

dahréntråd
Part of LWW Group

isodraht
Part of LWW Group

ślaska
Part of LWW Group

利里达尔线材
liljedahl wire
Part of LWW Group