



# DAROGLAS 155 AL

Rectangular conductor of aluminium, covered with glassfibre-polyester yarn, class 155

**Product name:**

Daroglas 155 1 AL  
Daroglas 155 2 AL

**Properties:**

- Excellent resistance to mechanical stress
- Very good adhesion to conductor

**Specifications:**

Internal LWW or customer specification

**Field of application:**

- Dry-type transformers
- Electric motors

**UL approval:**

Not approved

**Standard packaging:**

Drum 500 and 630

**Class: 155**

Temperature index  $\geq 155^{\circ}\text{C}$  acc. to experience  
Heat shock:  $\geq 175^{\circ}\text{C}$

**Shelf life:**


5 years, under normal ambient conditions

**Insulation:**

1-2 layers of polyester glass fibre yarn

**Conductor material**

EN 1715 - EN AW1370 [Al 99.7]



T - t = Increase in thickness

W - w = Increase in width

**Conductor corner radius**

Nominal thickness of conductor (mm)		Corner radius (mm)	Tolerance
Over	Up to and including		
-	1,00	0,5 nominal thickness	+/- 25%
1,00	1,60	0,50	+/- 25%
1,60	2,24	0,65	+/- 25%
2,24	3,55	0,80	+/- 25%
3,55	-	1,00	+/- 25%

**Conductor tolerances**

Nominal width or thickness of the conductor (mm)		Tolerance +/- (mm)
Over	Up to and including	
-	3,15	0,030
3,15	6,30	0,050
6,30	12,50	0,070
12,50	-	0,100

Certified according to ISO 9001, IATF 16949, ISO 14001

# DAROGLAS 155 AL

Rectangular conductor of aluminium, covered with glassfibre-polyester yarn, class 155

## Insulation increase

Designation	Nominal width of conductor	Increase in thickness	Increase in width
Daroglas 155 1 AL	$2,00 \leq w \leq 3,15$	$0,12 \pm 0,04$	max. 0,16
	$3,15 < w \leq 6,30$	$0,14 \pm 0,04$	max. 0,18
	$6,30 < w \leq 12,50$	$0,16 \pm 0,05$	max. 0,21
	$12,50 < w \leq 20,50$	$0,18 \pm 0,06$	max. 0,24
Daroglas 155 2 AL	$2,00 \leq w \leq 3,15$	$0,25 \pm 0,06$	max. 0,31
	$3,15 < w \leq 6,30$	$0,28 \pm 0,07$	max. 0,35
	$6,30 < w \leq 12,50$	$0,30 \pm 0,08$	max. 0,38
	$12,50 < w \leq 20,50$	$0,32 \pm 0,08$	max. 0,40


## Properties for DAROGLAS 155 AL

Main characteristics	Test method	Interval	Acceptance criteria
<b>Electrical properties</b>			
Conductor resistance	IEC 60851 - 5.3	1)	$0,02817 \Omega \text{mm}^2/\text{m}$
Conductivity	1/R	1)	$> 35,5 \text{ m}/(\Omega \text{mm}^2)$
Breakdown voltage	IEC 60851 - 5.4	All sizes	350 V
- Daroglas 155 1 AL - Daroglas 155 2 AL			560 V
<b>Mechanical properties</b>			
Elongation	IEC 60851-3.3	$t \leq 3,15$	$\geq 15\%$
		$t > 3,15$	$\geq 20\%$
Flexibility		All sizes	10 x thickness
- Bending flatwise			
Adherence	IEC 60851-3.5	All sizes	10 % stretch, no loss of adhesion
-Stretch			

1. Dependence of dimension is expressed by the unit

## Dimension range

### DAROGLAS AL



The technical data included is up to date at the time of printing.

LWW reserves the right to make any amendments deemed necessary

Ed.A(3)